


PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B29C 47/02	A1	(11) International Publication Number: WO 97/11831 (43) International Publication Date: 3 April 1997 (03.04.97)
(21) International Application Number: PCT/US96/14397 (22) International Filing Date: 9 September 1996 (09.09.96) (30) Priority Data: 08/533,592 25 September 1995 (25.09.95) US (71) Applicant: GENERAL ELECTRIC COMPANY [US/US]; 1 River Road, Schenectady, NY 12345 (US). (72) Inventors: BOLON, Donald, Allen; 2030 Cook Road, Charl- ton, NY 12019 (US). BAUMGARTNER, Charles, Edward; 945 Mohegan Road, Schenectady, NY 12309 (US). IRWIN, Patricia, Chapman; 1097 Knox Cave Road, Altamont, NY 12009 (US). (74) Agents: STECKLER, Henry, I. et al.; General Electric Com- pany, 3135 Easton Turnpike W3C, Fairfield, CT 06431 (US).		(81) Designated States: JP, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published With international search report.

(54) Title: EXTRUDED THERMOPLASTIC INSULATION ON STATOR BARS



(57) Abstract

An apparatus and a method provide for the extruding of thermoplastic insulation onto complex shapes, such as generator stator bars (38). The method of the present invention comprises the steps of feeding the complex shape (38) through a central bore of an extrusion die (10) to deposit a thermoplastic coating (10) along the entire length of the shape as the extrusion die (10) traverses the length of the complex shape (38).

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

EXTRUDED THERMOPLASTIC INSULATION ON STATOR BARS

Background of the Invention

This invention relates to an apparatus and a method for applying insulation to power generator stator bars and the resulting stator bars. More particularly, it relates to an apparatus and a method for extruding thermoplastic insulation onto stator bars, an extrusion die and the stator bar comprising thermoplastic insulation that is produced by the method.

Stator bars conduct current out of the generator. Typically, a generator comprises a rotor that rotates in a magnetic field, thereby inducing an electrical field in a conductor. The stator bar is the conductor.

These stator bars typically comprise numerous strands of copper bundled together. The stator bars are manufactured in various lengths, shapes and cross sections, depending on the generator design, voltage and power. The stator bars of each generator are unique, being custom designed for the specific generator. Generators can contain more than 100 stator bars. The stator bars can be up to 30 feet long and several inches in width.

Because of the high voltage carried by these stator bars, they must be insulated electrically from the rest of the stator. Typically, high voltage insulation for generator stator bars is made by a taping process. Multiple layers of any thermosetting epoxy/mica/glass tape are wrapped around the stator bar and then covered with subsequent layers of a sacrificial polymer that protects the insulation layers during later processing. The wrapped stator bars are then heated under vacuum to remove most of the residual solvent from the epoxy resin. The epoxy resin is cured under pressure using conditions that are designed to allow the epoxy to flow sufficiently to fill any voids present in the wrapped layers. In a different process, multiple layers of mica containing tape are wrapped around the stator

- 2 -

bar. Then, in a subsequent operation, the bar is vacuum dried to remove air and volatiles followed by pressure impregnation with an epoxy or silicone material. While providing an excellent electrical insulation when properly manufactured, these processes are very time consuming and labor intensive. Also, because of the variable processing parameters, such as time, temperature, and pressure, needed to balance the proper amount of solvent release and the degree of epoxy flow prior to full cure of the epoxy resin, these systems are prone to producing an insulation that is incompletely cured or possesses residual voids.

It is desirable to have an insulation that meets the thermal, mechanical and electrical property requirements of the stator bar environment and that can be applied to the stator bar using a method that leaves it essentially free of voids. Therefore, it is desirable to use a thermoplastic material as insulation. It is also desirable to provide a method of applying insulation that is not so labor intensive, and therefore, is cheaper, while at the same time offering thermal and electrical properties that are better than those available with the process of the prior art.

Using extruded thermoplastic as insulation on wiring is well known in the art. Typically, wire is coated by an extrusion head wherein the wire is passed through a central bore within the extrusion head. This central bore is coaxial with one or more annular extrusion mandrels that deposit concentric layers of thermoplastic, such as polyethylene, onto the wire as it passes through the extrusion head. The walls of the central bore are typically parallel to the direction of movement of the wire so that the wire is held substantially straight within the extrusion head. Such an extrusion head cannot accommodate a wire that is not flexible or is not "straight" in the sense that it can be placed into the extrusion head parallel to the direction of the movement of the wire. A wire coating extrusion head is typified by the die disclosed in US Patent 4,940,504 wherein a plurality of layers of plastic compounds are extruded onto a moving electrical conductor which is centered in the plastic coating.

- 3 -

It is desirable to provide an extrusion head that can coat wires or bars which are not flexible enough to be coated through an extrusion head of the prior art. More particularly, it is desirable to provide an extrusion head that can accommodate bars of varying
5 geometric shapes.

Summary of the Invention

The present invention provides a method of extruding
10 thermoplastic material onto a complex shape comprising the steps of:
a. feeding the complex shape with a length
and more than one side into a central bore of a die wherein said
central bore is of a configuration sufficient to allow said die to be
moved along said complex shape,

15 b. extruding at least one thermoplastic
material through said die so that it is deposited simultaneously onto
each side of said complex shape;

c. traversing said die along the entire length
of said complex shape.

20 The present invention also provides an apparatus for
applying insulation to a complex shape comprising:

a. a central bore of a die wherein said central
bore is of a configuration sufficient to allow said die to be moved
along a complex shape with a plurality of sides and a length, and
25 through which said complex shape is fed.

b. a means of traversing said extrusion die
along the length of said complex shape.

c. at least one extruder connected to said die
by flexible coupling means.

30 The present invention further provides a die for
extruding at least one thermoplastic material onto a complex shape
wherein the die comprises a central bore of a shape sufficient to allow
said die to be moved along the length of a complex shape.

- 4 -

The present invention finally provides a stator bar for power generation equipment comprising extruded thermoplastic insulation on each of a plurality of sides.

5

Brief Description of the Drawings

Fig. 1 is a schematic diagram of the present invention generally illustrating its major components.

Fig. 2 is a schematic diagram of a cross section of the preferred embodiment of the die.

10

Description of the Preferred Embodiment

This invention relates to extrusion of thermoplastic insulation onto complex shapes. More particularly, it relates to extrusion of thermoplastic insulation onto stator bars for power generators.

15

Extrusion dies are well known in the art. Many designs of extrusion dies used to coat wire or to extrude a parison for blow molding can be adapted for use in the present invention. As shown in Fig. 2, one embodiment of an extrusion die, indicated generally at 10, in accordance with the invention includes one or more extrusion mandrels indicated generally at 12 and 14 through which flow streams of plastic 16 and 18 onto a complex shape 38, such as a stator bar. There must be at least one extrusion mandrel 12. Additional mandrels can be added to allow for the development of a multilayer plastic coating 40 on the complex shape 38.

20

25

There is no limit on the design of the portion of the extrusion mandrels 12 and 14 that determines the flow pattern of the plastic stream(s) 16 and 18. The configuration of multiple extrusion mandrels can be similar to that disclosed in US Patent 4,940,504, hereby incorporated by reference, wherein the extrusion mandrels comprise concentric segments whereby the plastic streams are mechanically and thermally separated. Another acceptable extrusion

30

- 5 -

mandrel design is disclosed in US Patent 5,069,612, hereby incorporated by reference, wherein the extrusion die 10 comprises one or more coaxial annular extrusion mandrels 12 and 14 each including a pair of mating annular members with central frustoconical portions having apexes with an axial dimension greater than the axial dimension of the outer portions of the mandrels so as to form air spaces around each mandrel including frustoconical air space portions to avoid direct heat transfer between adjacent mandrels. The extrusion die 10 design can also be similar to that disclosed in US Patent 4,182,603, hereby incorporated by reference, wherein the extrusion die 10 is of the type known as a spiral mandrel die wherein the extrusion mandrels 12 and 14 are provided with helical grooves on their peripheries and wherein at least one spiral mandrel has helical grooves of opposite hand than those of the remaining mandrels.

While the design of the extrusion mandrels 12 and 14 can be varied as desired, it is imperative that the extrusion mandrels 12 and 14 have a central bore 20 of a configuration sufficient to allow the complete die 10 to be moved along the length of the complex shape 38. While the central bore 20 must allow the die 10 to be moved along the complex shape 38, it must also allow the extruded plastic stream(s) 16 and 18 to contact the complex shape 38 so that the plastic adheres to the shape 38. Preferably, as shown in Fig. 2, the central bore 20 is conical with the exit(s) 22 and 24 for the plastic stream(s) 16 and 18 at the narrow end of the cone 26 and the complex shape 38 moves through the cone from the wide end 28 toward the narrow end of the cone 26. Only this narrow end of the cone 26 is in close proximity to all sides of the shape, while the wide end of the cone 28 provides space for the shape to move within the die 10 to accommodate its irregular configuration.

The narrow end of the cone 26 can be any configuration, depending on the complex shape 38 to be covered. It can be circular or oval or it can conform to the cross section of the complex shape 38 over which it traverses. The configuration of the

- 6 -

narrow end of the cone will help to determine the thickness of the insulation. For some applications, it may be necessary to custom design a narrow end of the cone 26 that conforms substantially to the cross sectional configuration of the complex shape 38.

5 The method of the present invention comprises the steps of feeding the complex shape 38 through a central bore 20 of the extrusion die 10 to deposit a thermoplastic coating 40 along the entire length of the shape 38. This method is illustrated in Fig. 1.

 A complex shape 38 is fed through a central bore 20 of
10 an extrusion die 10. There is no limit on the configuration of the complex shape 38. Preferably, the complex shape 38 comprises a stator bar of a generator. Such stator bars can comprise numerous strands of copper bundled together. They are manufactured in various lengths, shapes and cross sections, depending on the
15 generator design, voltage and power. The stator bars can be up to 30 feet long and several inches in width.

 The complex shape 38 must be held by means sufficient to keep the complex shape 38 in a proper position relative to the die 10 as the die 10 traverses the length of the complex shape
20 38 while not interfering with the movement of the die 10 along the complex shape 38. Such means can hold the complex shape 38 stationary as the die traverses it. Means which provide for the movement of the shape 38 relative to the die 10 as the die 10 moves along the shape 38 can also be used. Such means will allow the
25 complex shape 38 to be moved about within the central bore 20 of the die 10, thereby allowing easier passage of the die 10 along the shape 38.

 The extrusion die 10 is made to traverse the length of the complex shape 38 by means sufficient to ensure that the die 10
30 follows the contours of the complex shape 38. Such means can include, but are not limited to, a track that follows the configuration of the complex shape 38 along which the extrusion die 10 can be propelled. Preferably, the die 10 traverses the length of the complex shape 38 by robotic means 36. These robotic means 36 can then be

- 7 -

used with any complex shape 38 simply by being reprogrammed to propel the die 10 along the contours of a particular complex shape 38.

At least one and preferably a plurality of extruders 32 and 34 supply molten plastic resin to the extrusion die 10. The number of extruders used is dependent on the number of layers of different plastics desired to produce the thermoplastic coating 40. Extruders 32 and 34 are well known in the art. There is no limit on the type of extruder 32 and 34 that can be used. Because the extrusion die 10 must move in more than one plane to traverse the length of a complex shape, it is important that the plurality of extruders 32 and 34 be attached to the extrusion die 10 by flexible coupling means 42 and 44. Such flexible coupling means 42 and 44 must be able to withstand the temperature and pressures of the molten plastic as it leaves the extruder 32 and 34. The flexible coupling means 42 and 44 can comprise thermally heated hose. Thermally heated hose that can withstand temperatures and pressures up to 760°C and 10 MPa is available commercially.

As depicted in Fig. 2, the plastic coating 40 that is applied to all sides of the complex shape 38 may comprise a plurality of layers made from the plurality of individual plastic streams 16 and 18 that are extruded from the plurality of die mandrels 12 and 14. The number of individual layers of thermoplastic is determinable by those skilled in the art, depending on the requirements of the particular application. For use in the present invention, the thermoplastic material must be able to withstand the temperatures at which the coated complex shape will operate. Polyetherimide is one example of one such material.

As diagrammed in Fig. 1, the apparatus for applying a thermoplastic coating to a complex shape comprises an extrusion die 10 through which a shape 38, with a plurality of sides and a length is fed, a means 36 of traversing the extrusion die 10 along the length of the complex shape 38, a plurality of extruders 32 and 34 connected to the die 10 by flexible coupling means 42 and 44.

- 8 -

What is claimed is:

1. A method of extruding thermoplastic material onto a complex shape comprising the steps of:
 - a. feeding the complex shape with a length and more than one side into a central bore of a die wherein said
5 central bore is of a configuration sufficient to allow said die to be moved along said complex shape,
 - b. extruding at least one thermoplastic material through said die so that it is deposited simultaneously onto each side of said complex shape;
 - 10 c. traversing said die along the entire length of said complex shape.
2. A method in accordance with claim 1, wherein said complex shape comprises a generator stator bar.
3. A method in accordance with claim 1, wherein said central bore is conical and comprises a narrow end, a wide end and at least one exit for at least one plastic stream at the narrow end of the central bore, and wherein said complex shape moves through
5 the central bore from the wide end toward the narrow end.
4. A method in accordance with claim 3, wherein said central bore comprises a plurality of exits for a plurality of plastic streams.
5. A method in accordance with claim 1, wherein said complex shape is supported by means sufficient to hold said shape stationary as said extrusion die traverses it.
6. A method in accordance with claim 1, wherein said complex shape is supported by means which provide for the movement of said complex shape relative to said extrusion die as said extrusion die moves along said complex shape.
7. A method in accordance with claim 1, wherein said extrusion die is traversed along the length of said complex shape by robotic means.
8. An apparatus for applying insulation to a complex shape comprising:

- 9 -

- 5 a. a central bore of a die wherein said central bore is of a configuration sufficient to allow said die to be moved along a complex shape with a plurality of sides and a length, and through which said complex shape is fed,
- b. a means of traversing said extrusion die along the length of said complex shape,
- 10 c. at least one extruder connected to said die by flexible coupling means.
9. An apparatus in accordance with claim 8, wherein said complex shape comprises a generator stator bar.
10. An apparatus in accordance with claim 8, wherein said central bore is conical and comprises a narrow end, a wide end and a plurality of exits for a plurality of plastic streams at the narrow end of the central bore, and wherein said complex shape moves
- 5 11. An apparatus in accordance with claim 8, wherein said complex shape is supported by means sufficient to hold said complex shape stationary as said extrusion die traverses it.
12. An apparatus in accordance with claim 8, wherein said complex shape is supported by means which provide for the movement of said complex shape relative to said extrusion die as said extrusion die moves along said complex shape.
13. An apparatus in accordance with claim 8, wherein said extrusion die is traversed along the length of said complex shape by robotic means.
14. An apparatus in accordance with claim 8, further comprising at least one extruder attached to said extrusion die by flexible coupling means that are capable of withstanding the temperature and pressures of molten plastic.
15. An apparatus in accordance with claim 8, further comprising a plurality of extruders attached to said extrusion die by flexible coupling means that are capable of withstanding the temperature and pressures of molten plastic.

- 10 -

16. A die for extruding at least one thermoplastic material onto a complex shape wherein the die comprises a central bore of a shape sufficient to allow said die to be moved along the length of a complex shape.

17. A die in accordance with claim 16, wherein said central bore is conical and comprises a narrow end, a wide end and at least one exit for at least one plastic stream at the narrow end of the central bore, and wherein said complex shape moves through the
5 central bore from the wide end toward the narrow end.

18. A die in accordance with claim 17, wherein said central bore further comprises a plurality of exits for a plurality of plastic streams.

19. A stator bar for power generation equipment comprising at least one thermoplastic material extruded onto each of a plurality of sides.

20. A stator bar in accordance with claim 19, wherein said thermoplastic material comprises polyetherimide.

21. A stator bar in accordance with claim 19, further comprising a plurality of thermoplastic materials extruded onto each of a plurality of sides.





fig. 1

2/2

*fig. 2*

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 96/14397

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 B29C47/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B29C H01B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP,A,0 638 408 (SAINT GOBAIN VITRAGE) 15 February 1995 see abstract see column 4, line 17 - column 5, line 10 see column 6, line 47 - line 52 see claims 1-4; figures 1,3	1-14
A	---	15
Y	GB,A,1 064 622 (SUMITOMO ELECTRIC INDUSTRIES LTD) 5 April 1967 see page 2, line 53 - line 111 see figures 5,6	1,3-8, 10-14 16-18
A	---	
	--- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- *A* document member of the same patent family

Date of the actual completion of the international search

10 December 1996

Date of mailing of the international search report

17.12.96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl.
Fax (+ 31-70) 340-3016

Authorized officer

Jensen, K

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 96/14397

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,Y	US,A,5 552 222 (BOLON DONALD A ET AL) 3 September 1996 see column 1, line 48 - line 61 see column 2, line 9 - line 14 see claims 1-4	2,9
A	---	19-21
P,A	EP,A,0 689 925 (TOKAI KOGYO CO LTD) 3 January 1996 see page 6, line 16 - line 27 see figures 4,9	1,6,8,12
A	---	
A	DE,A,38 31 321 (ROKADO METALL HOLZ KUNSTSTOFF) 22 June 1989 see column 2, line 50 - line 62 see claim 4; figure 1	1,6,8,12
A	---	
A	PATENT ABSTRACTS OF JAPAN vol. 004, no. 111 (M-025), 9 August 1980 & JP,A,55 069436 (IKEGAI CORP), 26 May 1980, see abstract	1,3,6,8, 10,12, 16,17
A	---	
A	DE,A,26 29 114 (KUNSTSTOFFFABRIK ERICH DITTRICH) 12 January 1978 see claims 1,5; figure 1 -----	1,8,16

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No
PCT/US 96/14397

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0638408	15-02-95	DE-A- 4326650 CZ-A- 9401930 JP-A- 7165441 US-A- 5507994	16-02-95 15-11-95 27-06-95 16-04-96
GB-A-1064622		NONE	
US-A-5552222	03-09-96	NONE	
EP-A-0689925	03-01-96	JP-A- 4261822 DE-D- 69118852 DE-T- 69118852 DE-D- 69118854 DE-T- 69118854 EP-A- 0493068 EP-A- 0493069 US-A- 5411696 US-A- 5498391	17-09-92 23-05-96 26-09-96 23-05-96 26-09-96 01-07-92 01-07-92 02-05-95 12-03-96
DE-A-3831321	22-06-89	DE-U- 8716369	04-02-88
DE-A-2629114	12-01-78	NONE	

THIS PAGE BLANK (USPTO)
